



**Staaltemperaturen onbeklede profielen na 30 minuten standaardbrand**




IPE		
80	836	833
100	835	832
120	834	830
140	833	828
160	831	826
180	830	823
200	828	820
220	826	815
240	822	810
270	820	805
300	817	800
330	811	793
360	805	783
400	799	775
450	791	768
500	782	759
550	772	752
600	762	745




HEA		
100	822	799
120	822	799
140	819	790
160	814	781
180	811	775
200	804	765
220	795	755
240	783	745
260	778	742
280	772	739
300	761	735
320	752	733
340	748	731
360	745	728
400	741	725
450	738	723
500	736	719
550	736	721
600	736	721
650	735	721
700	734	719
800	734	721
900	733	719
1000	733	719

**Staaltemperaturen onbeklede profielen na 30 minuten standaardbrand**



HEB		
100	810	775
120	801	762
140	791	752
160	778	743
180	768	737
200	758	734
220	751	731
240	745	725
260	742	721
280	740	719
300	736	708
320	734	701
340	733	701
360	732	697
400	730	693
450	727	693
500	723	688
550	723	693
600	723	693
650	723	693
700	721	693
800	721	697
900	719	697
1000	719	701



HEM		
100	739	719
120	736	711
140	734	701
160	730	688
180	725	679
200	719	663
220	714	658
240	679	610
260	674	602
280	669	593
300	632	546
320	632	556
340	632	556
360	639	566
400	645	576
450	652	593
500	658	602
550	669	617
600	674	625
650	679	639
700	684	645
800	693	658
900	697	669
1000	704	679